This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.


Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.

THIS PAGE BLANK (USPTO)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 0 819 706 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication: 21.01.1998 Bulletin 1998/04

(51) Int. Cl.⁶: **C08F 10/00**, C08F 4/602

(21) Application number: 96111719.9

(22) Date of filing: 19.07.1996

(84) Designated Contracting States:

AT BE CH DE DK ES FR GB GR IE IT LI LU MC NL
PT SE

(71) Applicant: FINA TECHNOLOGY, INC. Dallas, Texas 75206 (US)

(72) Inventors:

- Shamshoum, Edwar S. Houston, Texas 77062 (US)
- Bauch, Christopher G.
 Seabrook, Texas 77586 (US)

- Reddy, B.R. Baytown, Texas 77520 (US)
- Rauscher, Davis J.
 Angleton, Texas 77515 (US)
- McGovern, Kevin P.
 Friendswood, Texas 77546 (US)
- (74) Representative:
 Detrait, Jean-Claude et al
 c/o Fina Research S.A.
 Patent Department
 Zone Industrielle C
 7181 Feluy (BE)

(54) Process for the syndiotactic propagation of olefins

(57) The invention provides a process for commercial production of syndiotactic polyolefins using a metal-locene catalyst supported on silica treated with MAO. The invention includes contacting the supported metal-locene catalyst with an aluminum alkyl and aging the catalyst prior to polymerization. In addition, the catalyst is prepolymerized in a tubular reactor prior to being introduced into the polymerization reaction zone.

Description

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION: This invention relates to a catalyst and process for polymerization of olefins. A supported metallocene catalyst is made by treating a support with an alumoxane co-catalyst and complexing a metallocene with the alumoxane. The supported metallocene catalyst is suspended in a diluent. Prior to the introduction into a polymerization reaction zone, the supported metallocene catalyst is contacted with an aluminum alkyl co-catalyst.

<u>DESCRIPTION OF THE PRIOR ART</u>: Catalysts for the syndiotactic polymerization of olefins are known in the art and have been known at least since U.S. Patent No. 3,305,538, which described use of a catalyst to produce small quantities of syndiotactic polypropylene which were extracted. Since that time, patents have issued relating to organometallic or metallocene catalysts which produce syndiotactic polyolefins. Examples of these patents include U.S. Patent Nos. 4,892,851; 5,132,381; 5,187,250; 5,219,968 and 5,225,507, the disclosures of which, together with the disclosure of U.S. Patent No. 3,305,538, are hereby incorporated by reference.

These patents disclose metallocene catalysts that are basically a complex derived from a cyclopentadiene, i.e., a metal derivative of cyclopentadiene, which has been ionized by an ionizing agent to form an active cationic metallocene catalyst. It has also become known in the art that metallocenes may be supported on an inert non-reactive material.

In the U.S. Patent No. 4,701,432 a support is treated with at least one metallocene and at least one non-metal-locene transition metal compound. To form a catalyst system a co-catalyst comprising an alumoxane and an organo-metallic compound of Group IA, IIA, IIB and IIIA is added to the supported metallocene/non-metallocene. The support is a porous solid such as talc or inorganic oxides or resinous materials, preferably an inorganic oxide, such as silica, alumina, silica-alumina, magnesia, titania or zirconia, in finely divided form. By depositing the soluble metallocene on the support material it is converted to a heterogeneous supported catalyst. The transition metal compound, such as TiCl₄, is contacted with the support material prior to, after, simultaneously with or separately from contacting the metallocene with the support.

In U.S. Patent No. 4,897,455 a metallocene and an alumoxane were reacted in the presence of a support material to provide a supported metallocene-alumoxane reaction product as a catalyst to polymerize olefins, preferably ethylene. The support is a porous solid, such as talc, inorganic oxides and resinous support materials, such as a polyolefin, and is preferably silica, alumina, silica-alumina and mixtures thereof.

In U.S. Patent No. 4,935,397 a silica gel having a particle size less than 10 microns containing from about 5 to about 20 per cent by weight absorbed water as a catalyst support material. The silica gel is coated with alumoxane and a metallocene is complexed with the alumoxane to form a catalyst which can be used in high pressure and/or high temperature olefin polymerization.

In U.S. Patent No. 5,200,379 pentadienyl derivatives were complexed with transition metals to form a catalyst which is supported on activated inorganic refractory compounds, preferably inorganic oxides and metal phosphates, such as silica and alumina. The inorganic refractory compounds are activated by calcining in air at elevated temperatures and then contacted with a pentadienyl derivative - transition metal complex, such as bis(2,4-dimethylpentadienyl)titanium. The supported catalyst can be used in olefin, preferably ethylene, polymerization.

In U.S. Patent No. 5,240,894 a metallocene is activated with methylalumoxane (MAO) to form a reaction product which is contacted with dehydrated silica. After drying, a supported catalyst is formed which can be used in polymerization of olefins, particularly propylene, a trialkylaluminum co-catalyst or scavenger can be used in polymerization to minimize fouling and increase catalyst activity.

SUMMARY OF THE INVENTION

The invention provides a process for syndiotactic propagation in the polymerization of olefins, particularly propylene. In one embodiment, the invention comprises forming a suspension of the supported metallocene catalyst in an inert liquid carrier, such as mineral oil, contacting the supported metallocene catalyst with a trialkylaluminum, such as tri-isobutyl aluminum, co-catalyst and introducing the catalyst into a polymerization reaction zone which contains a monomer solution. A preferred embodiment includes forming a supported metallocene catalyst on an inert, non-reactive support, such as silica.

In another embodiment, the invention comprises pre-polymerizing the catalyst with the co-catalyst and an olefin. The olefin is added after the catalyst has contacted the co-catalyst. The catalyst is then introduced into the reaction zone. It is preferred to have a stream of olefin contact the catalyst and co-catalyst and carry the catalyst into the reaction zone.

In another embodiment of the invention, the catalyst is contacted with the co-catalyst, for a certain period of time. The catalyst and co-catalyst are suspended in an inert liquid carrier, such as mineral oil. The catalyst is then contacted with an olefin prior to introducing the catalyst into the reaction zone.

30

40

45

In the pre-polymerization step, the catalyst may be coated with a polymer product such that the weight ratio of polymer/catalyst is approximately 0.01-3.0. Preferably, the ratio of coating the catalyst is greater than 1.0 and, more preferably, 2.0-3.0. The preferred olefin is propylene.

The preferred catalyst comprises a metallocene compound of the general formula:

 $R''_{b}(CpR_{5-b}) CpR'_{5-b})MR^*_{v-2}$

where R" is a bridge imparting stereorigidity to the structure to the metallocene by connecting the two cyclopentadienyl rings, b is 1 or 0 indicating whether the bridge is present or not, Cp is a cyclopentadienyl ring, R and R' are substituents on the cyclopentadienyl rings and can be a hydride or a hydrocarbyl from 1-9 carbon atoms, each R and R' being the same or different, each (CpR_{5-b}) and (CpR'_{5-b}) being different so that bilateral symmetry exists, M is a Group IIIB, IVB, VB or VIB metal, R* is a hydride, a halogen or a hydrocarbyl from 1-20 carbon atoms, v is the valence of M. The preferred co-catalyst is an alkylaluminum compound, and most preferably tri-isobutyl aluminum.

BRIEF DESCRIPTION OF THE DRAWINGS

5

20

25

A more complete appreciation of the invention and many of the attendant advantages thereof will be readily understood by reference to the following detailed description when considered in connection with the accompanying drawing wherein:

Figure 1 is a schematic illustration of the invention as used in supplying a prepolymerized catalyst system to a continuous flow reactor used for the polymerization of propylene in the liquid phase.

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides a process for syndiotactic propagation in the polymerization of α -olefins. The invention is particularly adapted for the polymerization of propylene. The invention includes contacting the supported metallocene catalyst with an aluminum alkyl co-catalyst and then prepolymerizing prior to introducing the catalyst into a polymerization reaction zone. Another embodiment of the invention includes contacting the catalyst with the co-catalyst for a certain period of time (aging). Test results show an increase in efficiency of the catalyst of up to 6250 gms polymer product/gm catalyst in one hour when it is aged with the co-catalyst as taught by the present invention. In a preferred embodiment, the aged catalyst is prepolymerized prior to being introduced into the reaction zone.


The type of catalyst contemplated for use in the present invention is generally a metallocene catalyst. These catalysts can be generally defined as a cyclopentadienide, i.e., a metal derivative of cyclopentadiene, which has been ionized to form an active cationic metallocene catalyst. The metallocene compound generally contains two cyclopentadienyl rings and is of the general formula:

R"_b(CpR_{5-b}) (CpR'_{5-b})MR*_{v-2}

where R" is a bridge imparting stereorigidity to the structure to the metallocene by connecting the two cyclopentadienyl rings, b is 1 or 0 indicating whether the bridge is present or not, Cp is a cyclopentadienyl ring, R and R' are substituents on the cyclopentadienyl rings and can be a hydride or a hydrocarbyl from 1-9 carbon atoms, each R and R' being the same or different, each (CpR_{5-b}) and (CpR'_{5-b}) being different so that bilateral symmetry exists, M is a Group IIIB, IVB, VB or VIB metal, R* is a hydride, a halogen or a hydrocarbyl from 1-20 carbon atoms, v is the valence of M. Preferably the bridge R" is present and is a hydrocarbyl biradical of 1-20 carbon atoms. Hydrocarbyl radicals useful as the bridge in the present catalysts include linear all radicals of 1-10 carbon atoms or branched alkyl radicals of 1-20 carbon atoms, preferably one carbon atom, which may be substituted or unsubstituted, preferably substituted. The bridge is most preferably diphenylmethyl. (CpR_{5-b}) is preferably an unsubstituted cyclopentadienyl ring. (CpR'_{5-b}) is preferably a substituted cyclopentadienyl ring, more preferably a cyclopentadienyl ring substituted such that the substituents are radicals bonded to adjacent carbon atoms to form a fused ring, most preferably (CpR'_{5-b}) is fluorenyl. Preferably, M is a Group IVB metal, more preferably, titanium, zirconium or hafnium. R* is preferably a halogen or an alkyl, more preferably, chlorine or methyl.

Bilateral symmetry is defined as the condition in which there are no substituents or one or more substituents on one side and no substituents or one or more substituents on the other side in the same relative position such that a mirror image is formed from one side to another. One example of such a compound is isopropyl (cyclopentadienyl-9-fluorenyl)zirconium dichloride, abbreviated iPr(Cp)(Flu)ZrCl₂. An illustration of the ligands of this compound are shown below:

Bilateral symmetry is illustrated by a plane bisecting the zirconium metal and the bridge resulting in the right side of each ligand being a mirror image of its left side. The α and β position of the cyclopentadienyl ring represent the position of possible substituents in the proximal and distal position, respectively, or positions 2/5 and 3/4 of the drawing below:



It is believed that bilateral symmetry must exist for the β substituents of the cyclopentadienyl ring but is of less importance and may not be necessary for the α substituents of the cyclopentadienyl ring. It is further believed that bilateral symmetry of substituents of the fluorenyl ring is of less importance and may not be necessary. It is believed that bilateral symmetry of less importance and may not be necessary for the bridge.

The alumoxanes useful in combination with the metallocene compound of the present invention may be represented by the general formula $(R-Al-0-)_n$ in the cyclic form and $R(R-Al-0-)_nALR_2$ in the linear form wherein R is an alkyl group with one to five carbon atoms and n is an integer from 1 to about 20. Most preferably, R is a methyl group and the preferred alumoxane is methylalumoxane (MAO). The alumoxanes can be represented structurally as follows:

The support was silica having high surface area and small average pore size. One example of silica operative in this invention is chromatography grade silica. The silica was treated with methylalumoxane (MAO) in the following manner: The silica had water removed to a level of approximately 1.0%. The dried silica was slurried in a nonpolar solvent. A solution of alumoxane in solvent was added to the silica slurry. After heating and subsequently cooling the slurry, the

solid (silica treated with alumoxane) was separated out and (optionally) dried.

The metallocene was contacted with the MAO-treated silica to form a supported metallocene catalyst in the following manner: A solution of metallocene in a nonpolar solvent was added to a slurry of silica treated with alumoxane also in a nonpolar solvent, preferably the same solvent as the metallocene solution. The solid, metallocene supported on silica treated with alumoxane, was separated out and dried.

A suspension was formed with the supported metallocene catalyst in an inert liquid carrier, such as mineral oil. The liquid carrier is selected based on the following properties:

- 1. The liquid does not dissolve the solid catalyst component.
- 2. The liquid has minimal chemical interaction with the catalyst component.
- 3. The liquid is preferably an inert hydrocarbon.

10

25

- 4. The liquid only "wets" the catalyst component
- 5. The liquid has sufficient viscosity to maintain the catalyst component in suspension without excessive agitation.

Liquids which would be effective in this invention would be long chain hydrocarbons, such as mineral oil and polyisobutylene. This listing is not intended to be complete and all inclusive but is merely made to show examples of useful liquid media.

A co-catalyst is utilized to aid in the activation of the catalyst for the polymerization reaction. The most commonly used co-catalyst is an organoaluminum compound which is usually an alkyl aluminum. The aluminum alkyl is of the general formula AIR'3 where R' is an alkyl of from 1-8 carbon atoms or a halogen and R' may be the same or different with at least one R¹ being an alkyl. Examples of aluminum alkyls are trialkyl aluminums, such as trimethyl aluminum (TMA), triethyl aluminum (TEAI) and triisobutyl aluminum (TiBAI). The organoaluminum may also be a dialkylaluminum halide, such as diethyl aluminum chloride (DEAC), or an alkylaluminum dihalide. The preferred co-catalyst is an aluminum trialkyl, specifically triisobutyl aluminum ("TIBAI").

In order to increase the efficiency of the catalyst, the catalyst is pre-polymerized. Basically, the pre-polymerization reaction occurs as a monomer is introduced into a mixture of catalyst and co-catalyst. The monomer is polymerized, and in so doing, it adheres to the surface of the catalyst and forms a coating. Any known method for prepolymerizing a catalyst can be used for the catalyst of the present invention.

In pre-polymerizing the catalyst, a weight ratio of polymer/catalyst of approximately 0.01-3.0 is desirable. Preferably, the weight ratio of polymer to catalyst is greater than 1.0. The preferred range of polymer coating to catalyst is approximately 2.0-3.0.

According to one embodiment of the invention, the supported metallocene catalyst is contacted with a co-catalyst and then is prepolymerized by contact with the monomer prior to being introduced into a polymerization reaction zone which contains additional monomer. In a preferred embodiment, the contact of the catalyst with the co-catalyst occurs in a holding tank in which the catalyst/co-catalyst mixture is allowed to age for 1 hour to 720 hours (30 days), preferably 18 to 48 hours and more preferably 12 to 24 hours. The catalyst/co-catalyst mixture may be fed into the reactor in a continuous or periodic manner.

The contact of the catalyst/co-catalyst mixture with the monomer for prepolymerization can take place in a pipe which carries the catalyst into the polymerization zone. The contact time or residence time of the catalyst in the pipe need be only a few seconds. A minimum of three seconds of pre-contact between the catalyst/co-catalyst and the monomer is sufficient to significantly increase the efficiency of the catalyst. The concentration of co-catalyst in the stream may be varied as the co-catalyst is transferred into the polymerization reaction zone. A preferred concentration would be less than 10% co-catalyst. All of the co-catalyst necessary for the polymerization reaction in the reaction zone need not be fed through this contact pipe. A portion of the desired amount of co-catalyst in the reactor may be added directly to the reaction zone.

It was found that there was a relationship between aging the catalyst in aluminum alkyl and prepolymerization in so far as obtaining polymer product with desirable morphology. The morphology of the polymer product is a function of the particle size, particle shape and the particle size distribution of the catalyst particles. In most processing applications it is desirable for the polymer to have morphology in which the particle are granular rather than agglomerated. To obtain these granular particles it was found that the aging time of the catalyst in aluminum alkyl could be decreased or eliminated if the prepolymerization time was increased and, conversely, the prepolymerization could be decreased (but not eliminated) as the aging time increased. In addition, it was found that the amount of aluminum alkyl used in aging the catalyst affected polymer morphology. As the relative amount of aluminum alkyl was increased for the same aging time period, the morphology improved.

The invention having been generally described, the following examples are given as particular embodiments of the invention and to demonstrate the practice and advantages thereof. It is understood that the examples are given by way of illustration and are not intended to limit the specification or the claims to follow in any manner.

Preparation of the Metallocene

A manipulations were carried out under argon using standard Schlenk techniques unless otherwise noted.

5 Ph₂C(Flu-Cp)⁴:

To a solution of 50g fluorene in 200ml anhydrous tetrahydrofuran at room temperature was added dropwise at 0°C, 207 ml of a 1.6 molar solution of n-butyllithium in hexane (Fig.4). The reaction mixture was stirred for 1 hr at room temperature and cooled to -78°C upon which light brown solid precipitated. 69.3 g of diphenylfulvene was then added to the reaction mixture. The heterogeneous mixture was allowed to gradually come to room temperature with constant stirring and was stirred at room temperature overnight (~18 hrs). The reaction mixture was cooled to 0°C and cautiously quenched with dilute hydrochloric acid (10 to 18%) (slightly exothermic). The mixture was stirred at 0°C for 5 minutes and diluted with 300 ml water and 200ml hexane and filtered through a medium frit funnel. The resulting solid was washed with water (500 ml) followed by hexane (300 ml). The resulting wet solid was air dried followed by drying under vacuum with slight warming. To completely remove entrapped solvent the sample was heated at 100°C under high vacuum overnight. The yield of THF- and water-free ligand was in the range 70-80%.

Ph2C(Flu-Cp)ZrCl2;

20

25

35

55

A three-necked 3L flask equipped with mechanical stirrer and pressure equalized addition funnel (Fig.4) was charged with 73.2 g of rigorously dried ligand obtained from the previous method (It should be noted that, the ligand must be dry but not necessarily free of THF. In case, THF-free ligand is used, it appears that it may be advantageous to use excess of n-butyllithium to complete dianion formation). One liter of anhydrous ether was added and the stirring initiated. The slurry was cooled to 0°C, and 254.2 ml of 1.6 molar n-butylithium in hexane was added dropwise cautiously. The temperature of the reaction mixture was gradually allowed to come to room temperature and stirred overnight (~18h). The stirring was stopped and the solid was allowed to settle. The supernatant was decanted. The resulting solid was washed with two portions of anhydrous hexane (2 x 500 ml). A fresh batch of 1.0 L of anhydrous hexane was added and the stirring was initiated. The reaction mixture was cooled to 0°C and 42 g of ZrCl₄ was added in small portions. The temperature was allowed to come to room temperature and stirred overnight (18h). The stirring was stopped and the solid allowed to settle. The supernatant was decanted and the solid dried under vacuum. Total weight, 112 g (contains LiCl).

Purification Method

112 g of the crude product was added to a 3L, 3 neck-flask and 2 L amylene-free chloroform (amylene present as a preservative in chloroform was removed either by purging with argon for 20 min or by removal under vacuum for a few minutes followed by release of vacuum with argon and repetition of the process 3-4 times) was added. The mixture was magnetically stirred at room temperature for 45 min; the stirring stopped and the flask was placed in a warm water bath. The solid suspension was allowed to settle. Using a cannula, the supernatant was filtered through a fritted funnel packed (2/3 full) with glasswool (Fig. 11). After the filtration was complete the remaining solid was rinsed with additional CHCl₃ (or until the undissolved solid is pale colored) and the washings were filtered into the receiving flask. The solvent was removed from the filtrate and the resulting bright red solid, 101 g (>95% of theoretical recovery), was stored in the drybox (for NMR, see Fig. 12).

45 MAO Treatment of Silica

500 g of silica (Fuji-Davison - Chromatography Grade) was dried at 200°C in vacuo for two hours (Figure 1). Water content of the silica was determined by heating a sample of the dried silica to 300°C and calculating the percent loss of weight (approximately 0.5-1.08. Toluene (1.5 L) was added and the slurry stirred at room temperature. 1500 mL of a solution of 30% by weight of MAO in toluene was then added to the silica slurry. The slurry was then heated to reflux for 4 hours. After cooling to room temperature, the supernatant was decanted by cannula and the solid washed four times each with 500 mL portions of toluene. The solid was then dried in vacuo overnight at 80°C.

Supporting of Metallocene on MAO-Treated Silica

A toluene solution of metallocene [diphenylmethyl cyclopentadienyl-9-fluorenylzirconium dichloride, abbreviated Ph₂C(Flu-Cp)ZrCl₂ - 16 g] was added via cannula to a stirred slurry of MAO/SiO₂ from the previous procedure (approximately 800 grams) in 2 L toluene. Upon contact with the MAO/SiO₂, the red metallocene turns the solid deep purple.

The slurry was stirred for one hour at room temperature. The supernatant liquid was decanted and the solid washed three times each with 500 mL hexane. The purple solid was then dried overnight in vacuo at room temperature.

The following Examples and Comparative Examples illustrate the present invention in more detail and the advantages to be gained in increased catalyst efficiency by introducing a pre-polymerized catalyst into a reaction zone.

EXAMPLE I

A slurry of 180 mg solid catalyst component and 540 mg of triisobutylaluminum (TIBAI) was prepared in 5.0 ml mineral oil. A one ml aliquot was added to a 2.0 liter autoclave from which the air had been sufficiently replaced by nitrogen. The autoclave was then charged with 1.4 liters of liquid propylene and 16 mmoles of gaseous hydrogen. The mixture was then heated to 60°C and maintained for 60 minutes. The polymer was then dried at 80°C. Polymerization results are shown in Table 1.

Polymerization					
Reagents Conditions					
Catalyst: 36 mg	Temperature: 60°C				
TIBAI: 108 mg	Time: 1 hour				
Propylene: 1.4 L (0.72 kg)					
Hydrogen: 16 mmol					

EXAMPLE II

15

20

35

Approximately 16 mmoles of hydrogen were added to an empty (under ~ 2 psig nitrogen) and dry 2 L Zipperclave reactor followed by 1.0 L of propylene. The reactor was heated to 60°C and stirred at approximately 1000 rpm. A slurry of 180 mg solid catalyst component was prepared and mixed with 540 mg of triisobutylaluminum (TIBAI) in 5.0 ml mineral oil. A one ml aliquot was precontacted with a small amount of propylene at room temperature for five seconds. The catalyst was then charged into the reactor.

Polymerization continued for one hour during which time the reactor was maintained at the polymerization temperature. At the end of this time polymerization was terminated by rapidly venting the reactor of unreacted monomer. The polymer yield and analysis is shown in Table I.

EXAMPLE III

Approximately 16 mmoles of hydrogen ($_{0}P = 120$ psig from a 48.7 Ml bomb) were added to an empty (under $_{0}P = 120$ psig nitrogen) and dry 2 L Zipperclave reactor followed by 1.0 L of propylene. The reactor was heated to 60°C and stirred at approximately 1000 rpm. A slurry of 108 mg solid catalyst component and 45 mg of triisobutylaluminum (TIBAI) in 5.0 ml mineral oil were prepared and aged for one day. One ml of the mineral oil slurry was precontacted with 99 mg of TIBAI. The catalyst was then charged into the reactor.

Polymerization continued for one hour during which time the reactor was maintained at the polymerization temperature. At the end of this time polymerization was terminated by rapidly venting the reactor of unreacted monomer. The polymer yield and analysis is shown in Table I.

EXAMPLE IV

The same procedure of Example III was used except 60 mg of TIBAI was used for aging. The polymer yield and analysis is shown in Table I.

EXAMPLE V

Approximately 16 moles of hydrogen ($_0P = 120$ psig from a 48.7 Ml bomb) were added to an empty (under ~ 2 psig nitrogen) and dry 2 L Zipperclave reactor followed by 1.0 L of propylene. The reactor was heated to 60°C and stirred at approximately 1000 rpm.

A slurry of 108 mg solid catalyst component and 45 mg of triisobutylaluminum (TIBAI) in 5.0 ml mineral oil was prepared and aged for two days. A one ml aliquot of the mineral oil slurry was mixed with 99 mg of TIBAI. The mineral

oil/TIBAI mixture was precontacted with a small amount of propylene for 5 seconds. The catalyst was then charged into the reactor.

Polymerization continued for one hour during which time the reactor was maintained at the polymerization temperature. At the end of this time polymerization was terminated by rapidly venting the reactor of unreacted monomer. The polymer yield and analysis is shown in Table I.

EXAMPLE VI

The same procedure of Example V was used except 60 mg of TIBAI was used for aging.

EXAMPLE VII

10

The same procedure of Example V was used except the precontact time was 10 seconds.

15 EXAMPLE VIII

The same procedure of Example V was used except 60 mg of TIBAI was used for aging and the precontact time was 10 seconds.

20 EXAMPLE IX

The same procedure of Example III was used except 135 mg of TIBAI was used.

EXAMPLE X

25

The same procedure of Example III was used except 180 mg of TIBAI was used.

EXAMPLE XI

30 The same procedure of Example V was used except 135 mg of TIBAl was used for aging and the aging was one day.

EXAMPLE XII

The same procedure of Example V was used except 180 mg of TIBAI was used for aging and the aging was one day.

EXAMPLE XIII

The same procedure of Example V was used except 135 mg of TIBAL was used for aging, the aging was one day and the precontact time was 10 seconds.

EXAMPLE XIV

The same procedure of Example V was used except 180 mg of TIBAI was used for aging, the aging was one day and the precontact time was 10 seconds.

50

TABLE I

Example #	TIBAL mg	Aging (days)	Prepoly (sec)	Yield (g)	Efficiency (g sPP/g cat)	Bulk Density (g/cc)	Melt Flow (g/10 min)	Morphology	
1.	0	•	0	125	3472	0.32	0.56	Agglomerate	
2.	0	-	5	127	3528	0.32	0.56	Agglomerate	
3.	45	1	0	146	4056		0.56	Agglomerate	
4.	60	1	0	130	3611		-	Agglomerate	
5.	45	2	5	132	3667	٠	0.60	Agglomerate	
6.	60	2	5	126	3500		0.68	Agglomerate	
7.	45	2	10	128	3556	0.32	0.72	Granules	
8.	60	2	10	108	3000	0.31	0.70	Granules	
9.	135	1	0	145	4028	0.35	0.58	Agglomerate	
10.	180	1	0	146	4056		0.66	Agglomerate	
11.	135	1	. 5	145	4028	0.34	0.70	Agglomerate	
12.	180	1	5	128	3556	0.32	0.62	Granules & Agglomerate	
13.	135	1	10	192	5333	0.32	0.68	Granules	
14.	180	1	10	225	6250	0.35	-	Granules	

Polymer morphology is related to the prepolymerization time. The desired polymer morphology was obtained with a prepolymerization of at least 10 seconds. Polymer morphology is related to the amount of aluminum alkyl used in aging the catalyst. The desired polymer morphology was obtained with a catalyst aged in an aluminum alkyl to catalyst weight ratio of approximately 1:1 when triisobutyl aluminum was used as the aluminum alkyl.

Catalyst efficiency is related to activation of the catalyst with aluminum alkyl. Catalyst efficiency improved when the catalyst was aged in aluminum alkyl. In addition, catalyst efficiency is related to prepolymerization. Catalyst efficiency improved when the catalyst was prepolymerized at least 10 seconds, especially when the catalyst was aged in an aluminum alkyl to catalyst weight ratio of approximately 1:1 when triisobutyl aluminum was used as the aluminum alkyl.

The drawing is a schematic illustration showing the prepolymerization system of the present invention set up for the supply of prepolymerized catalyst to a continuous flow-type polypropylene reactor. The continuous flow reactor 2 normally will take the form of a loop 4 equipped with an impeller 5. As will be understood by those skilled in the art the impeller 5 functions to circulate the polymerization reaction mass continuously through the loop at controlled temperature and pressure conditions. The polymer product is withdrawn from the reactor via line 6.

A carrier stream for the prepolymerization reactor is initially established by the supply of a suitable solvent for the catalyst to a mixing line 8. The organic solvent, such as mineral oil, is supplied to the mixing line via line 9. TIBAI supplied to the carrier fluid from suitable sources (not shown) via lines 11 and 12, respectively. After addition of the co-catalyst, the catalyst is supplied to the carrier fluid via line 14. The catalyst may be supplied by any suitable procedure, either continuously or intermittently. The carrier fluid containing the catalyst components is then supplied to a tubular reactor 16 where it is mixed with liquid propylene supplied, for example, by a secondary line 18 leading from a main propylene supply line 19. The amount of propylene supplied to the prepolymerization reactor 16 is relatively small in comparison to the amount of propylene supplied via the main supply line 19 to the polymerization reactor 2. The propylene supplied to the prepolymerization reactor 16 and also the main reactor 2 normally will have small amounts of hydrogen entrained therein.

As noted previously, because of the perceived slow reaction time of the prepolymerization reaction, the residence times of the propylene and catalyst components in prior art prepolymerization reactors are normally on the order of minutes or even hours. Also the capacity of the prepolymerization reactor in a commercial unit is fairly substantial, normally on the order of 200 liters or more. In the present invention, the residence time of the reaction mixture within the prepolymerization reactor 16 is less than a minute and, as practical matter on the order of several seconds, and the volume capacity of the prepolymerization reactor will be quite small, normally less than 1 liter. For most applications of the invention, the residence time within the prepolymerization reactor is approximately three seconds. The temperature of

5

10

15

20

the tubular reactor is less than the polymerization temperature but sufficient to prepolymerize the catalyst and is preferably no greater than 30°C.

The drawing illustrates the preferred order of addition of the catalyst components to the carrier stream. That is, it is desirable that the catalyst which already contains the co-catalyst be added to the carrier stream.

In a specific embodiment of the invention, the catalyst component is supplied to an elongated tubular prepolymerization reactor of extremely low capacity which is operated at a residence time of approximately three seconds.

In this embodiment, reaction chamber 16 is defined by a 50-200 feet long tubing having an internal diameter of 3/8 inch and is preferably 100 feet. The flow rate is adjusted to provide for a residence time within the tubing of approximately three seconds.

Obviously, numerous modifications and variations of the present invention are possible in light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described herein.

Claims

5

10

15

20

25

30

35

40

45

50

55

A process of treating silica with an alumoxane comprising:

removing water from the silica; slurring the silica in a nonpolar solvent; adding a solution of alumoxane in solvent to the silica slurry; heating to reflux and subsequently cooling the slurry to room temperature; and separating a solid silica treated with alumoxane from the slurry.

- 2. A process as in Claim 1 wherein the water is removed to a level of approximately 1.0%.
- 3. A process as in Claim 1 wherein the silica is chromatography grade silica.
- 4. A process as in Claim 1 wherein the alumoxane is represented by the general formula (R-Al-0-)_n in the cyclic form and R(R-Al-0-)_nALR₂ in the linear form wherein R is an alkyl group with one to five carbon atoms and n is an integer from 1 to about 20.
- 5. A process as in Claim 1 wherein the alumoxane is methylalumoxane.
- 6. A process as in Claim 1 wherein the nonpolar solvent is toluene.
- 7. A process as in Claim 1 wherein after the solid silica treated with alumoxane is separated from the slurry additionally comprising:

drying the solid silica treated with alumoxane.

8. A process for supporting a metallocene on a solid treated with alumoxane comprising:

forming a solution of a metallocene of the general formula

$$R''_{b}(CpR_{5-b}) (CpR'_{5-b})MR'_{v-2}$$

where R" is a bridge imparting stereorigidity to the structure to the metallocene by connecting the two cyclopentadienyl rings, b is 1 or 0 indicating whether the bridge is present or not, Cp is a cyclopentadienyl ring, R and R' are substituents on the cyclopentadienyl rings and can be a hydride or a hydrocarbyl from 1-9 carbon atoms, each R and R' being the same or different, each (CpR_{5-b}) and (CpR'_{5-b}) being different so that bilateral symmetry exists between (CpR_{5-b}) and (CpR'_{5-b}) , M is a Group IIIB, IVB, VB or VIB metal, R* is a hydride, a halogen or a hydrocarbyl from 1-20 carbon atoms, v is the valence of M in a nonpolar solvent forming a slurry of silica treated with alumoxane in a nonpolar solvent;

adding the two slurries together at room temperature;

stirring the resulting slurry;

separating the solid;

drying the solid.

- 9. A process as in Claim 8 wherein the bridge is a hydrocarbyl biradical having 1-20 carbon atoms.
- 10. A process as in Claim 8 wherein the bridge is a single substituted carbon atom.
- 11. A process as in Claim 8 wherein the bridge is a linear alkyl radicals of 1-10 carbon atoms or branched alkyl radicals of 1-20 carbon atoms.
 - 12. A process as in Claim 8 wherein the bride is diphenylmethyl.
- 10 13. A process as in Claim 8 wherein (CpR_{5-b}) is unsubstituted cyclopentadienyl.
 - 14. A process as in Claim 8 wherein (CpR'5-b) is fluorenyl.
 - 15. A process as in claim 8 wherein Me is a Group IVB metal.
 - 16. A process as in Claim 8 wherein Me is zirconium.
 - A process as in Claim 8 wherein the metallocene is diphenylmethyl(cyclopentadienyl-9-fluorenyl)zirconium dichloride.
 - 18. A process as in Claim 8 wherein the nonpolar solvent is toluene.
 - 19. A process for activating a metallocene supported on a silica treated with alumoxane comprising:
- forming a suspension of a metallocene catalyst supported on silica treated with alumoxane in an inert liquid carrier; and adding an organoaluminum.
 - 20. The process as in Claim 19 additionally comprising:
 - aging the mixture of the metallocene catalyst supported in silica treated with alumoxane and the organoaluminum 1 to 720 hours.
 - 21. A process as in Claim 19 wherein the bridge is a hydrocarbyl biradical having 1-20 carbon atoms.
 - 22. A process as in Claim 19 wherein the bridge is a single substituted carbon atom.
 - 23. A process as in Claim 19 wherein the bridge is a linear alkyl radicals of 1-10 carbon atoms or branched alkyl radicals of 1-20 carbon atoms.
 - 24. A process as in Claim 19 wherein the bride is diphenylmethyl.
 - 25. A process as in Claim 19 wherein (CpR_{5-b}) is unsubstituted cyclopentadienyl.
- 26. A process as in Claim 19 wherein (CpR'_{5-b}) is fluorenyl.
 - 27. A process as in Claim 19 wherein Me is a Group IVB metal.
 - 28. A process as in Claim 19 wherein Me is zirconium.
 - 29. A process as in Claim 19 wherein the metallocene is diphenylmethyl(cyclopentadienyl-9-fluorenyl)zirconium dichloride.
- 30. The process as in Claim 19 wherein the organoaluminum is an alkyl aluminum of the general formula AIR'₃ where
 R' is an alkyl of from 1-8 carbon atoms or a halogen and R' may be the same or different with at least one R¹ being an alkyl.
 - 31. The process as in Claim 30 wherein the organoaluminum is an trialkyl aluminum, a dialkylaluminum halide, or an

15

20

30

35

alkylaluminum dihalide.

5

10

15

25

30

40

45

50

55

- 32. The process as in Claim 31 wherein the organoaluminum is trimethyl aluminum, triethyl aluminum, triisobutyl aluminum or diethyl aluminum chloride.
- 33. The process as in Claim 32 wherein the organoaluminum is triisobutyl aluminum.
- 34. A process for polymerization of olefins comprising:
 - (a) contacting a supported metallocene catalyst with an organoaluminum compound, said catalyst being of the general formula:

R"_b(CpR_{5-b}) CpR'_{5-b})MR'_{v-2}

where R" is a bridge imparting stereorigidity to the structure to the metallocene by connecting the two cyclopentadienyl rings, b is 1 or 0 indicating whether the bridge is present or not, Cp is a cyclopentadienyl ring, R and R' are substituents on the cyclopentadienyl rings and can be a hydride or a hydrocarbyl from 1-9 carbon atoms, each R and R' being the same or different, each (CpR_{5-b}) and (CpR'_{5-b}) being different so that bilateral symmetry exists between (CpR_{5-b}) and (CpR'_{5-b}), M is a Group IIIB, IVB, VB or VIB metal, R* is a hydride, a halogen or a hydrocarbyl from 1-20 carbon atoms, v is the valence of M;

- (b) prepolymerizing the catalyst with an olefin monomer.
- (c) introducing said catalyst into a polymerization reaction zone containing an olefin monomer.
- 35. A process as in Claim 34 wherein the bridge is a hydrocarbyl biradical having 1-20 carbon atoms.
- 36. A process as in Claim 35 wherein the bridge is a single substituted carbon atom.
- 37. A process as in Claim 36 wherein the bridge is a linear alkyl radicals of 1-10 carbon atoms or branched alkyl radicals of 1-20 carbon atoms.
- 38. A process as in Claim 37 wherein the bride is diphenylmethyl.
- 39. A process as in Claim 34 wherein (CpR_{5-b}) is unsubstituted cyclopentadienyl.
- 35 40. A process as in Claim 34 wherein (CpR'_{5-b}) is fluorenyl.
 - 41. A process as in Claim 34 wherein Me is a Group IVB metal.
 - 42. A process as in Claim 34 wherein Me is zirconium.
 - 43. The process of Claim 34 where the metallocene is isopropyl (cyclopentadienyl-9-fluorenyl)zirconium dichloride.
 - **44.** The process of Claim 34 wherein the catalyst is pre-polymerized by contacting the catalyst with a monomer prior to the polymerization reaction zone.
 - 45. The process of Claim 34 wherein the contact of the catalyst with the organoaluminum compound in step (a) occurs for about 1 hour to about 720 hours.
 - 46. The process of Claim 34 wherein the contact of the catalyst with the organoaluminum compound is 18 to 48 hours.
 - 47. The process of Claim 34 wherein the contact of the catalyst with the organoaluminum compound is 12 to 24 hours.
 - 48. The process of Claim 34 wherein the pre-polymerized catalyst is coated such that the weight ratio of polymeric to catalyst is approximately 0.01-3.0.
 - 49. The process of Claim 48 wherein the weight ratio of polymer to catalyst is greater than 1.0.
 - 50. The process of Claim 49 wherein the weight of polymer to catalyst is approximately 2.0-3.0.

- 51. The process as in Claim 34 wherein the organoaluminum is an alkyl aluminum of the general formula AIR'₃ where R' is an alkyl of from 1-8 carbon atoms or a halogen and R' may be the same or different with at least one R¹ being an alkyl.
- 5 52. The process as in Claim 51 wherein the organoaluminum is an trialkyl aluminum, a dialkylaluminum halide, or an alkylaluminum dihalide.
 - 53. The process as in Claims 52 wherein the organoaluminum is trimethyl aluminum, triethyl aluminum, triisobutyl aluminum or diethyl aluminum chloride.
 - 54. The process as in Claim 53 wherein the organoaluminum is triisobutyl aluminum.
 - 55. The process of Claim 34 wherein the monomer is propylene.
- 56. The process of Claim 34 wherein the catalyst is suspended in an inert liquid carrier.
 - 57. The process of Claim 56 wherein said inert liquid carrier is mineral oil.
 - 58. The process of Claim 34 wherein the pre-polymerizing is a minimum of three seconds.
 - 59. A process for supplying catalyst to an olefin polymerization reactor comprising:
 - (a) establishing a fluid carrier stream containing a supported metallocene catalyst of the general formula:

R"_b(CpR_{5-b}) CpR'_{5-b})MR*_{v-2}

where R" is a bridge imparting stereorigidity to the structure to the metallocene by connecting the two cyclopentadienyl rings, b is 1 or 0 indicating whether the bridge is present or not, Cp is a cyclopentadienyl ring, R and R' are substituents on the cyclopentadienyl rings and can be a hydride or a hydrocarbyl from 1-9 carbon atoms, each R and R' being the same or different, each (CpR_{5-b}) and (CpR_{5-b}) being different so that bilateral symmetry exists between (CpR_{5-b}) and (CpR_{5-b}) , M is a Group IIIB, IVB, VB or VIB metal, R* is a hydride, a halogen or a hydrocarbyl from 1-20 carbon atoms, v is the valence of M;

- (b) adding olefin monomer to the carrier stream containing the catalyst;
- (c) flowing the carrier stream containing the olefin monomer and the catalyst through an elongated tubular reactor at a flow rate sufficient to provide a residence time in said tubular reactor of approximately three seconds under temperature conditions to prepolymerize the catalyst with the monomer within said tubular reactor without plugging of the tubular reactor; and
- (d) passing the carrier stream containing the prepolymerized catalyst into a polymerization reactor.
- 40 60. The process of Claim 59 wherein the volume capacity of the tubular reactor is less than 1 liter.
 - 61. The process of Claim 59 wherein the tubular reactor is 50-200 feet long with an internal diameter of 3/8 inch.
 - 62. The process of Claim 61 wherein the tubular reactor is 100 feet long.
 - 63. The process of Claim 59 wherein the olefin monomer is propylene.
 - 64. The process of Claim 59 wherein the tubular reactor is operated at a temperature no greater than 30°C.
- 50 65. The process of Claim 59 wherein the catalyst is prepolymerized such that the weight ratio of polymer to catalyst is approximately 0.01-3.0.
 - 66. The process of Claim 65 wherein the weight ratio is greater than 1.0.
- 55 67. The process of Claim 66 wherein the weight ratio is 2.0-3.0.
 - 68. A process of polymerization of olefins comprising:

10

20

25

30

35

(a) establishing a fluid carrier stream;

10

15

20

25

30

35

40

45

50

55


(b) adding a supported metallocene catalyst of the general formula:

R"_b(CpR_{5-b}) CpR'_{5-b})MR*_{v-2}

where R" is a bridge imparting stereorigidity to the structure to the metallocene by connecting the two cyclopentadienyl rings, b is 1 or 0 indicating whether the bridge is present or not, Cp is a cyclopentadienyl ring, R and R' are substituents on the cyclopentadienyl rings and can be a hydride or a hydrocarbyl from 1-9 carbon atoms, each R and R' being the same or different, each (CpR_{5-b}) and (CpR'_{5-b}) being different so that bilateral symmetry exists between (CpR_{5-b}) and (CpR'_{5-b}) , M is a Group IIIB, IVB, VB or VIB metal, R* is a hydride, a halogen or a hydrocarbyl from 1-20 carbon atoms, v is the valence of M,

wherein the catalyst has been aged with an organoaluminum compound;

- (c) allowing the aged catalyst to contact a co-catalyst and an olefin to prepolymerize the catalyst; and
- (d) introducing the carrier stream containing the prepolymerized catalyst into a polymerization reaction zone containing an olefin monomer.
- 69. The process of Claim 68 wherein the olefin monomer is propylene.
- 70. The process of Claim 68 wherein the prepolymerization is at a temperature no greater than 30°C.
- 71. The process of Claim 68 wherein the catalyst is prepolymerized such that the weight ratio of polymer to catalyst is approximately 0.01-3.0.
- 72. The process of Claim 71 wherein the weight ratio is greater than 1.0.
- 73. The process of Claim 72 wherein the weight ratio is 2.0-3.0.





EUROPEAN SEARCH REPORT

EP 96 11 1719

Category		DERED TO BE RELEVA indication, where appropriate, ssages	Re	evant claim	CLASSIFICATION (II	
x	EP-A-0 619 325 (FIN		1,4	-6,8, 15, 18, 25,		
	* page 5, line 31 - * page 4, line 40 - * page 5, line 51 -	line 58 *				-
x	EP-A-0 563 834 (MIT	SUI)		,11,		•
Y	* page 9, line 33 -	line 45; example 1 *	13- 1,4	16,18 -7		
x	EP-A-0 526 955 (EXX	on)	8,1 16,	3,15,		
Y	* page 18; example	X *	1,4			
X	EP-A-0 633 272 (SPH	ERILENE)	8,9 15,	,11,		
			18,	19,	TECHNICAL FU SEARCHED	ELDS (Int.Cl.6)
			27, 30- 37, 42,	28, 35, 41, 44, 54,	C08F	
Y	* page 11 - page 12	; examples 2-5 *	59-		•	
Y	EP-A-0 279 153 (FIN * claims 1,6,10,34 * page 11, line 1 - * page 12, line 29	*' - line 48 *	59-	73		
	The present search report has b	ocen drawn up for all claims Date of completion of the sourch			Exant ner	
	THE HAGUE	18 December 19	96	Fis	cher, B	
Y: par do: A: tec O: no	CATEGORY OF CITED DOCUME rticularly relevant if taken alone rticularly relevant if combined with an cument of the same category chnological background n-written disclosure ermediate document	E: earlier paten after the fill other D: document ci L: document ci	t documen ng date ted in the s ted for othe	t, but publ application or reasons	ished on, or	



EUROPEAN SEARCH REPORT

Application Number EP 96 11 1719

Category	Citation of document with in of relevant pa	ndication, where appropriate, ssages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CL6)
X	EP-A-0 704 461 (MIT	SUI)	1,4-7, 19,27, 28, 30-34, 41,42, 44, 48-56,58	
	* page 13, line 14	- line 50; example 1 *	10 00,00	
(EP-A-0 439 964 (MIT	SUI)	34,41, 42,44, 51-54, 56,58	
	* examples 14,15 *		30,30	
K	EP-A-0 668 295 (UNI * page 9, line 40 -		8-19, 21-33	
	* page 10, line 19 * page 14; examples	- line 29 *		TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			·	·
	·			
	The present search report has b	een drawn up for all claims	7	_
	Place of searck	Date of completion of the search		Examiner
	THE HAGUE	18 December 1996	5 Fis	cher, B
X : par Y : par doc A : tec	CATEGORY OF CITED DOCUME ticularly relevant if taken alone ticularly relevant if combined with an turnent of the same category hnological background n-written disclosure	E : earlier patent d after the filing other D : document cited L : document cited	ocument, but publi date in the application for other reasons	shed on, or

THIS PAGE BLANK (USPTO)